





**Internal transmittance  $\tau_i$  at reference thickness  $d$  [mm] = 3**  
**The internal transmittance values, tabulated and graphically represented, are reference values only**

$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$	$\lambda$ [nm]	$\tau_i$
200	< 1.0E-05	500	< 1.0E-05	800	9.8E-01	1100	9.7E-01	2200	9.7E-01	3700	3.3E-01
210	< 1.0E-05	510	< 1.0E-05	810	9.8E-01	1110	9.7E-01	2250	9.7E-01	3750	3.4E-01
220	< 1.0E-05	520	< 1.0E-05	820	9.8E-01	1120	9.7E-01	2300	9.7E-01	3800	3.5E-01
230	< 1.0E-05	530	< 1.0E-05	830	9.7E-01	1130	9.7E-01	2350	9.7E-01	3850	3.6E-01
240	< 1.0E-05	540	< 1.0E-05	840	9.7E-01	1140	9.7E-01	2400	9.7E-01	3900	3.6E-01
250	< 1.0E-05	550	< 1.0E-05	850	9.7E-01	1150	9.7E-01	2450	9.7E-01	3950	3.7E-01
260	< 1.0E-05	560	< 1.0E-05	860	9.7E-01	1160	9.7E-01	2500	9.6E-01	4000	3.6E-01
270	< 1.0E-05	570	< 1.0E-05	870	9.7E-01	1170	9.8E-01	2550	9.6E-01	4050	3.5E-01
280	< 1.0E-05	580	< 1.0E-05	880	9.7E-01	1180	9.8E-01	2600	9.6E-01	4100	3.3E-01
290	< 1.0E-05	590	< 1.0E-05	890	9.7E-01	1190	9.8E-01	2650	9.6E-01	4150	3.1E-01
300	< 1.0E-05	600	< 1.0E-05	900	9.7E-01	1200	9.8E-01	2700	9.2E-01	4200	2.8E-01
310	< 1.0E-05	610	< 1.0E-05	910	9.7E-01	1250	9.8E-01	2750	6.1E-01	4250	2.4E-01
320	< 1.0E-05	620	< 1.0E-05	920	9.7E-01	1300	9.8E-01	2800	4.3E-01	4300	1.9E-01
330	< 1.0E-05	630	< 1.0E-05	930	9.7E-01	1350	9.8E-01	2850	4.0E-01	4350	1.4E-01
340	< 1.0E-05	640	< 1.0E-05	940	9.7E-01	1400	9.8E-01	2900	4.0E-01	4400	9.3E-02
350	< 1.0E-05	650	1.5E-05	950	9.7E-01	1450	9.9E-01	2950	4.0E-01	4450	5.0E-02
360	< 1.0E-05	660	3.4E-04	960	9.7E-01	1500	9.9E-01	3000	3.9E-01	4500	2.3E-02
370	< 1.0E-05	670	6.3E-03	970	9.7E-01	1550	9.9E-01	3050	3.7E-01	4550	1.0E-02
380	< 1.0E-05	680	7.5E-02	980	9.7E-01	1600	9.9E-01	3100	3.5E-01	4600	4.0E-03
390	< 1.0E-05	690	3.4E-01	990	9.7E-01	1650	9.9E-01	3150	3.2E-01	4650	1.5E-03
400	< 1.0E-05	700	6.6E-01	1000	9.7E-01	1700	9.9E-01	3200	3.0E-01	4700	5.3E-04
410	< 1.0E-05	710	8.5E-01	1010	9.7E-01	1750	9.9E-01	3250	2.8E-01	4750	2.2E-04
420	< 1.0E-05	720	9.3E-01	1020	9.7E-01	1800	9.9E-01	3300	2.7E-01	4800	1.1E-04
430	< 1.0E-05	730	9.6E-01	1030	9.7E-01	1850	9.9E-01	3350	2.6E-01	4850	5.6E-05
440	< 1.0E-05	740	9.7E-01	1040	9.7E-01	1900	9.8E-01	3400	2.5E-01	4900	3.1E-05
450	< 1.0E-05	750	9.8E-01	1050	9.7E-01	1950	9.8E-01	3450	2.6E-01	4950	1.6E-05
460	< 1.0E-05	760	9.8E-01	1060	9.7E-01	2000	9.8E-01	3500	2.7E-01	5000	< 1.0E-05
470	< 1.0E-05	770	9.8E-01	1070	9.7E-01	2050	9.8E-01	3550	2.8E-01	5050	< 1.0E-05
480	< 1.0E-05	780	9.8E-01	1080	9.7E-01	2100	9.8E-01	3600	3.0E-01	5100	< 1.0E-05
490	< 1.0E-05	790	9.8E-01	1090	9.7E-01	2150	9.8E-01	3650	3.1E-01	5150	< 1.0E-05